



solid solutions to better hardscapes

PO Box 70 • 32020 126th St • Princeton, MN 55371 • Tel 800-752-9326 • Fax 763-389-2725

SRW PP350

SRW Products Manufactures/Supplies a 100% Polypropylene, monofilament yarn called SRW PP350 offering optimum performance when used in stabilization applications. Produced from first quality raw material, they provide the perfect balance of strength and separation. The fabric will not rot or mildew, is non-biodegradable, and is resistant to damage from insects and rodents.

SRW PP350 meets or exceeds the physical property values listed below.

| Fabric Property | Test Method | Units | Minimum Average Roll Value |
|-----------------------|-------------|--------------------------------|----------------------------|
| Grab Tensile Strength | ASTM D 4632 | lbs/ft | 350x200 |
| Grab Elongation | ASTM D 4632 | % | 15x15 |
| Trapezoidal Tear | ASTM D 4533 | lbs/ft | 100x70 |
| CBR Puncture | ASTM D 6241 | lbs/ft | 800 |
| Percent Open Area | CEO-02215 | % | 6 |
| Permittivity | ASTM D 4491 | Sec-1 | .5 |
| Permeability | ASTM D 4491 | cm/sec | .14 |
| AOS | ASTM D 4751 | US Sieve | 40 |
| Water Flow | ASTM D 4491 | gpm/ft ² | 60 |
| UV Resistance | ASTM D 4355 | % Strength Retained @500 hours | 90 |
| Roll Size | | L x W ft (sy) | 12x300 6x300 |

Values Provided represent expected values at time of manufacture. This document provides the characteristic properties of the product described.