

Tel: 800-752-9326 Fax: 763-389-2725 SRWProducts.com PO Box 70 32005 126th St Princeton, MN 55371

SRW Pro Plus IV

To Whom It May Concern:

SRW Pro Plus IV is a superior quality, woven geotextile produced by needle punching non-woven threads into the weave to form a high strength fabric with better water permeability. The polypropylene fibers are specially formulated to resist UV light deterioration and are inert to commonly encountered soil chemicals. The fabric will not rot or mildew, is non-biodegradable, and is resistant to damage from insects and rodents.

Fabric Property	Test Method	Units	Minimum Average Roll Value
Weight (Typical)		oz/sy	4.1
Grab Tensile	ASTM D 4632	lbs.	105 x 80
Grab Elongation	ASTM D 4632	lbs.	15
Trap-Tear Strength	ASTM D 4533	lbs.	45 x 30
CBR Puncture	ASTM D 4833	lbs.	300
Mullen Burst Strength	ASTM D 3786	psi	240
Water Flow	ASTM D 4491	gpm/ft²	15
UV Resistance	ASTM D 4355	%	70 (after 2500 hrs)

SRW Pro Plus IV meets or exceeds the physical property values listed below.

Values Provided represent expected values at time of manufacture. This document provides the characteristic properties of the product described.

Regards,