



Tel: 800-752-9326
Fax: 763-389-2725
SRWProducts.com

PO Box 70
32005 126th St
Princeton, MN 55371

SRW MM403

SRW Products Manufactures/Supplies a 100% Polypropylene, monofilament yarn called SRW MM404 offering optimum performance when used in stabilization applications. Produced from first quality raw material, they provide the perfect balance of strength and separation. The fabric will not rot or mildew, is non-biodegradable, and is resistant to damage from insects and rodents.

SRW MM403 meets or exceeds the physical property values listed below.

Fabric Property	Test Method	Units	Minimum Average Roll Value
Grab Tensile Strength	ASTM D 4632	lbs./ft	425 x 350
Grab Elongation	ASTM D 4632	%	21
Trapezoidal Tear	ASTM D 4533	lbs./ft	145 x 125
CBR Puncture	ASTM D 6241	lbs./ft	1340
Wide Width Tensile	ASTM D 4595	lbs./ft	3240 x 2700
Percent Open Area	CEO-02215	%	6
Permittivity	ASTM D 4491	sec ⁻¹	.96
Permeability	ASTM D 4491	cm/sec	.046
AOS	ASTM D 4751	US Sieve	40
Water Flow	ASTM D 4491	gpm/ft ²	70
UV Resistance	ASTM D 4355	% Strength Retained @500 hours	90
Roll Size		L x W ft (sy)	15 x 300 (500)

Values Provided represent expected values at time of manufacture. This document provides the characteristic properties of the product described.