



Tel: 800-752-9326
Fax: 763-389-2725
SRWProducts.com

PO Box 70
32005 126th St
Princeton, MN 55371

6 Mil Poly Sheeting

To Whom It May Concern:

6 Mil Poly Sheeting is manufactured using polyethylene and meets ASTM D 4397-84 (standard specification for polyethylene sheeting for Construction, Industrial, and Agricultural applications) and is manufactured in the U.S.A.

Film Property	Test Method	Units	Minimum Average Roll Value
Dart Drop	ASTM D1709	Grams	260
Tensile Strength	ASTM D882	Lengthwise PSI	1,700
Tensile Strength	ASTM D882	Crosswise PSI	1,200
Elongation	ASTM D882	Lengthwise %	160
Elongation	ASTM D882	Crosswise %	250
WVTR	ASTM E96(perms)	Grams/100in ² - Day	0.13
WVTR	ASTM E96	Grams/100in ² - Day	0.23

Values provided represent expected values at time of manufacture. This document provides the characteristic properties of the product described.